BEST PRACTICE: HANDLING & FINISHING ABS-ESD7 PARTS



Overview

ABS-ESD7 (static dissipative) material is one of the many great materials available for use with Fortus systems. This paper will walk you through the handling considerations for ABS-ESD7, including finishing, safety and packaging guidelines.

Finishing

The most common finishing techniques required for this material are bonding and smoothing. For smoothing, sanding is the recommended method. As with all FDM materials, standard sanding processes can be followed. Note that this material, unlike our standard ABS materials, cannot be smoothed using the finishing touch station. ABS-ESD7 can easily be bonded using typical methods including solvents, epoxies, hot-air welding, ultrasonic welding and super glue.



An assembly fixture for electronics made from ABS-ESD7.

Safety

Safety note: Sanding this material will release carbon particles; the finisher must wear an N100 respirator (eye protection is preferred).

A carbon additive has been added to the base material to achieve the desired static dissipation of ABS-ESD7, introducing some safety considerations for people who will be handling the material. Carbon elements will be released into the air if this material is sanded. N100 respirators are rated for airborne carbon and must be worn while sanding this material. It is also important to always sand this material in a well-ventilated area away from anyone not wearing a mask. A sanding room with a dust-collection system or a paint booth is ideal. Refer to the MSDS sheet on the Stratasys website for additional safety data.

Packaging

To keep this material free from foreign particles, be sure it is not exposed to packing peanuts or other lint-type shipping materials. The best way to do this is to place it in a plastic bag for transportation.

Conclusion

ABS-ESD7 is a great new material from Stratasys. With basic understanding of common finishing operations, safety considerations and packaging concerns, this material and the part built from it will perform as designed.



A worker sands ABS-ESD7 next to a dust-collection system while wearing safety glasses, gloves and a respirator.



ABS-ESD7 parts are best transported in plasitc bags.



Stratasys | www.stratasys.com | info@stratasys.com

7665 Commerce Way Eden Prairie, MN 55344 +1 888 480 3548 (US Toll Free) +1 952 937 3000 (Intl) +1 952 937 0070 (Fax) 2 Holtzman St. Science Park, PO Box 2496 Rehovot 76124, Israel +972 74 745-4000 +972 74 745-5000 (Fax)



ISO 9001:2008 Certified

© 2009, 2014Stratasys Inc. All rights reserved. Stratasys, FDM and Fortus are registered trademarks and Fused Deposition Modeling, FDM Technology, Fortus 250mc, Fortus 360mc, Fortus 400mc, Fortus 900mc, Insight and Control Center are trademarks of Stratasys Inc., registered in the United States and other countries. ULTEM 9085 is a trademark of SABIC Innovative Plastics IP BV. All other trademarks are the property of their respective owners. Product specifications subject to change without notice. Fortus-BP-HandlingAndFinishingABS-ESD7Parts-03-14.

For more information about Stratasys systems, materials and applications, contact Stratasys Application Engineering at 1-855-693-0073 (toll free), +1 952-294-3888 (local/international) or ApplicationSupport@Stratasys.com.