

# Neo Featured Materials Overview

Material Name	Description	Category	Tensile Strength (ASTM D638M)	Elongation at Break (ASTM D638M)	Tensile Modulus (ASTM D638M)	HDT @ 0.46 MPa (ASTM D648)	Notched Izod Impact (ASTM D256A)	Color	Partner Page
<b>Somos® WaterShed XC 11122</b>	Versatile, good all-round polymer, very easy to use	●	50.4 MPa (at break)	15.5%	2,770 MPa	50 °C	25 J/m	Clear	<a href="#">WaterShed XC 11122</a>
<b>Somos® WaterClear Ultra 10122</b>	Versatile, easy to use, exceptional clarity	●	56 MPa (at break)	7.5%	2,880 MPa	47 °C	25 J/m	Clear	<a href="#">WaterClear Ultra 10122</a>
<b>Somos® WaterShed Black</b>	Versatile, good all-round polymer, very easy to use	●	50.4 MPa (at break)	15.5%	2,770 MPa	50 °C	25 J/m	Black	<a href="#">WaterShed Black</a>
<b>Somos® PerFORM</b>	Very high heat and stiffness, ceramic	●	68 MPa	1.1%	10,500 MPa	269 °C	17 J/m	White	<a href="#">PerFORM</a>
<b>Somos® PerFORM Reflect</b>	Very high heat and stiffness, ceramic, developed for PIV	●	63.3 MPa	0.8%	10,135 MPa	276 °C	17 J/m	Orange	<a href="#">PerFORM Reflect</a>
<b>Somos® Taurus</b>	High heat and toughness, thermoplastic like performance	●	46.9 MPa (at yield)	24%	2,310 MPa	62-91 °C	47.5 J/m	Charcoal	<a href="#">Taurus</a>
<b>Somos® EvoLve 128</b>	Very tough and durable with great surface finish	●	56.8 MPa (at yield)	11%	2,694 MPa	52 °C	39 J/m	White	<a href="#">EvoLve 128</a>
<b>Somos® WaterShed AF</b>	Print accurate, complex investment casting patterns with excellent surface finish	●	46 MPa	10%	2,460 MPa	50 °C	34 J/m	Clear	<a href="#">WaterShed AF</a>

Categories: ● Investment Casting ● General Purpose ● High Heat ● Tough ● Medical

# Neo Featured Materials Overview

Material Name	Description	Category	Tensile Strength (ASTM D638M)	Elongation at Break (ASTM D638M)	Tensile Modulus (ASTM D638M)	HDT @ 0.46 MPa (ASTM D648)	Notched Izod Impact (ASTM D256A)	Color	Partner Page
<b>Somos® 9120</b>	Versatile, good allround polymer, very easy to use	●	31 MPa	20%	1,350 MPa	n/a	51 J/m	Clear	<a href="#">9120</a>
<b>Somos® BioClear</b>	For non-implantable limited body contact (<24hr) medical and dental applications	●	50.4 MPa (at break)	15.5%	2,770 MPa	50 °C	25 J/m	Clear	<a href="#">BioClear</a>
<b>Somos® DMX SL-100</b>	Durable and tough for production of complex, hollow composite parts	●	29.7–32.1 MPa (at break)	12–28%	2,260–2,560 MPa	44 °C	0.61–0.71 J/m	Off white	<a href="#">DMX SL-100</a>

Categories: ● Investment Casting ● General Purpose ● High Heat ● Tough ● Medical